



Castrol Molub-Alloy 3136

Lubricating Grease for High Loads

Description

MOLUB-ALLOY™ 3136 has been designed for high loads under unfavorable ambient conditions. Due to its formulation and additives it is able to cope with the extremely high loads and shock loads present in the steel and construction industry as well as in mining and forestry.

- For the production of MOLUB-ALLOY 3136 lubricating grease a mixture of mineral oil and polymers is used which form a thick lubricating film suited to withstand shock loads and vibrations.
- The shear-stable thickener has an excellent sealing effect against impurities in case mechanical seals have failed or are missing all together (sealing grease collar at the bearing).
- Inhibitors against corrosion and oxidation improve the rust protection and aging resistance of the base oil.

Application

- Rolling bearings, all types of sliding bearings, spindles, joint couplings (except for high-speed precision couplings), running gears, cams as well as general grease lubricating points especially where loads are high and speeds low.
- The grease is applied to the lubricating points by a hand lubricator or via an automatic lubricating system which is suited for NLGI 1 greases.

Conditions of Use

- MOLUB-ALLOY 3136 should not be mixed with lubricating greases with different soap base.
- After changing over to MOLUB-ALLOY 3136 the lubricating intervals should be gradually extended to ensure a thorough removal of the previous grease.

Advantages

- Very good sealing effect due to its optimum adhesion.
- Selected EP additives ensure an excellent protection against wear and scuffing even in boundary and mixed friction areas; this feature is especially important during stop-and-go operation, low speeds and/or high loads and shock loads.
- These benefits result in economic savings: less repair work and fewer downtime periods, prolonged service life of machine components and extended relubrication intervals

Typical Characteristics

Name	Method	Units	Molub-Alloy 3136
DIN Classification	DIN 51502	-	KPF 1 K-20
Soap Base	-	-	Lithium
Worked Penetration (60 strokes @ 25°C / 77°F)	ISO 2137 / ASTM D217	0.1mm	310 - 340
Dropping point	ISO 2176 / ASTM D566	°C/°F	>180/>356
Base Oil Viscosity @ 40°C / 104°F	ISO 3104 / ASTM D445	mm ² /s	880
Base Oil Viscosity @ 100°C / 212°F	ISO 3104 / ASTM D445	mm ² /s	63
Viscosity Index	ISO 2909 / ASTM D2270	-	137
Oxidation Stability - Rotating Pressure Vessel test	ASTM D942 / DIN 51808	pressure drop psi	3.63
Water Resistance	DIN 51807-1	Rating	0 (Pass)
Rust Test - EMCOR (distilled water)	ISO 11007 / ASTM D6138	Rating	0/0 (Pass)
Four Ball Wear test - Wear Scar Diameter	DIN 51350-5E	mm	<180
Flow pressure @ -20°C / -4°F	DIN 51805	mBar	<850
Operating Temperature	-	°C	- 20 / +120

Subject to usual manufacturing tolerances.

Castrol Molub-Alloy 3136

23 Jul 2012

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol Industrial, Technology Centre , Whitchurch Hill , Pangbourne , Reading , RG8 7QR , United Kingdom

www.castrol.com/industrial