

Molub-Alloy Paste PG LF 15-1

High Performance paste for small gears

Description

Molub-Alloy Paste PG LF 15-1 is a fully synthetic Silica based paste with a Polyglycol base fluid. It is suitable for worm gear applications. It provides excellent low temperature properties as well as good EPDM compatibility.

Application

- Molub-Alloy Paste PG LF 15-1 is designed for the lifetime/extended lubrication of steel/plastic or plastic/plastic components
- Used in small gears in Electro Mechanical Power Brake systems.

Typical Characteristics

Name	Method	Units	Molub-Alloy Paste PG LF 15-1
Colour	Visual	-	White/Beige
Thickener Type	-	-	Silica
Base Oil	-	-	Polyglycol
Consistency	ISO 2137 / ASTM D217	NLGI Grade	1
Worked Penetration Grease @ 25 °C, 60 cycles	ASTM D217	1/10 mm	310 - 340
Dropping Point, Grease	ASTM D566	°C/°F	>200/>392
Base Fluid Viscosity @ 40 °C/104 °F	ISO 3104/ASTM D445	mm²/s	13
Base Fluid Viscosity @ 100 °C/212 °F	ISO 3104/ASTM D445	mm²/s	4
Dynamic viscosity @ 25 °C	DIN 51810 T1	mPas	900
Viscosity Index	ISO 2909/ASTM D2270	-	200
Density @ 20 °C/68 °F	IP 530	kg/m³	1200
Oil Separation 168 h/40 °C	DIN 51817	%	5
Oil Separation 18 h/40 °C	DIN 51817	%	3
Flow Pressure (Greases) -40 °C/-40 °F	DIN 51805	hPa	200

Subject to usual manufacturing tolerances.

Molub-Alloy Paste PG LF 15-1 09 May 2022

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.