



Product Data

Tribol GR ALR 100-00 PD

Robot Grease

Description

Castrol Tribol® GR ALR 100-00 PD high-performance grease is based on fully synthetic base oil and a Lithium complex thickener system, enhanced with the MicroFlux Trans (MFT) additive system.

Castrol's Microflux Trans (MFT) Plastic Deformation (PD) additive helps improve performance when operating temperature and loads reach a certain level of activation energy, by enabling the micro-smoothing of surface roughness without increasing wear. The smoothed surface delivers optimum wear protection and an extremely low coefficient of friction, especially in applications which experience extreme pressure, shock loads, vibrations or low speeds. This helps with extended lubricant life and prolong relubrication intervals.

MFT PD helps to protect against scuffing and shock loading, while maintaining a high load carrying capacity, and can help prevent the progression of micro-pitting in pre-damaged gears.

Application

Tribol GR ALR 100-00 PD was developed for use in robot gear systems where grease lubrication is preferred over lubrication by gear oil. The combination of synthetic base fluid and lithium complex thickener system and the MFT-PD additive system makes it particularly suited to a wide application temperature range.

Low temperature performance is accurately measured for this type of flow grease by Rheometer measurement down to -40°C designed for easier start up at low temperatures (Also measured in the low temperature torque test).

The MFT-PD additive system will help to maintain a stable backlash, which is required for high-precision robot-gears.

Tribol GR ALR 100-00 PD has a base oil viscosity of 100 mm²/s and an NLGI grade of 00. This combination provides a lower bleed rate than other commercially available greases avoiding oil leakages and a high base oil viscosity giving the gear box more protection.

Tested with various elastomer seal material (95°C for 1008 hours), Tribol GR ALR 100-00 PD has excellent elastomer compatibility.

Advantages

Compared to other commercially available robot greases Tribol GR ALR 100-00 PD has the following advantages:

- MFT-PD technology shown to reduce wear, friction and protect gear surfaces.
- Very low friction torque levels particularly suited for start-stop motion in robots, including at low temperatures.
- Very low oil separation reducing the potential for leakage.
- Excellent elastomer compatibility to prevent seal damage.
- Extended lubrication life-time and relubrication intervals.

Typical Characteristics

Name	Method	Units	Tribol GR ALR 100-00 PD
Colour	Visual	-	Brown
Thickener Type	-	-	Lithium Complex
Base Oil	-	-	Synthetic
Base Oil Viscosity @ 40 °C / 104 °F	ISO 3104 / ASTM D445	mm ² /s	100
Consistency	ISO 2137 / ASTM D217	NLGI Grade	00
Worked Penetration (60 strokes @ 25°C / 77°F)	ISO 2137 / ASTM D217	1/10 mm	400 - 430
Worked Penetration - 100,000 strokes; change from 60 strokes	ISO 2137 / ASTM D217	1/10 mm	+20
Roll Stability test - Shear Stability (50 hrs, 60°C / 140°F)	ASTM D1831 mod	1/10 mm	+10
Oil Separation (168 hrs @ 80°C / 176°F)	ASTM D6184 mod	% wt	20
Evaporation Loss (24 hrs @ 100°C / 212°F)	DIN 58397-1	% wt	1
Oxidation Stability	ASTM D942	psi	7
Copper Corrosion (24 hrs, 100°C / 212°F)	ASTM D4048	rating	1a
Rheometer Dynamic Viscosity @ -20°C / -4°F	in-house method	Pa s	15
Low Temperature Torque @ -40°C / -40°F - Starting / Running Torque	ASTM D1478	Nm	0.05 / 0.03
Four Ball Weld Load test - Weld Point	ISO 11008 / ASTM D2596	kgf	250+
Four Ball Weld Load test - Last Non Seizure Load	ISO 11008 / ASTM D2596	kgf	126
Four Ball Weld Load test - Load Wear Index (27°C / 80°F / 1770 rpm)	ISO 11008 / ASTM D2596	kgf	56
FE-8 Bearing Wear test (C/75/50) Rolling Elements (Mw50)	DIN 51819-2	mg	< 10
FE-8 Bearing Wear test (C/75/50) Friction Torque	DIN 51819-2	Nm	3

Subject to usual manufacturing tolerances

Tribol GR ALR 100-00 PD

31 Oct 2022

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

BP Lubricants USA Inc., 1500 Valley Road, Wayne, NJ 07470
 Telephone: +1-888-CASTROL Product Information: +1-877-641-1600
www.castrol.com/en_us/b2b/home.html