

Tribol™ OG 500-0

Spray Grease for Open Gears

Description

Castrol Tribol™ OG 500-0 (previously called Castrol Tribol™ 5000) with TGOA is a high-performance open gear grease. It was especially developed for application in cement, mining and other heavy industries, to assure proper tribo-technical and economical maintenance of open gears through automatic spray systems.

Castrol Tribol™ OG 500-0 differs from conventional asphaltic type open gear lubricants, as it does not contain solvents nor solids.

It has outstanding extreme pressure (EP) antiwear characteristics derived from the latest development in the field of surface improving additives designated TGOA.

The TGOA additive package performs better than other EP and antiwear additives because of its unique action on frictional surfaces.

Castrol Tribol™ OG 500-0 is approved by major original equipment manufacturers.

- Castrol Tribol™ OG 500-0 is manufactured from mineral oil, selected for optimum physical and chemical stability, blended with special adhesive agents and thickened with aluminum-complex soap.
- The TGOA additive package is activated by high specific loads and corresponding temperatures causing a chemical-physical reaction. This results in an equalization of surface roughness without creating abrasion. Therefore, surface roughness is reduced without the loss of surface material.
- The results of the TGOA additives can be compared with a rolling process in the micro-range. The surface roughness is gradually leveled and smoothed.
- The load carrying area is increased with increased safety loads on tooth flanks at reduced friction levels.
- If, because of shock loads or stop-and-go operation, surface roughness peaks redevelop, the TGOA additive package is automatically reactivated. Surface roughness is again equalized and lubrication optimized.

Application

- Castrol Tribol™ OG 500-0 is a high-performance lubricant for open gears, wire ropes and similar applications.
- Castrol Tribol™ OG 500-0 was developed for application through automatic spray systems, but may also be applied manually. Heat or the addition of thinners is unnecessary.
- Castrol Tribol™ OG 500-0 is recommended for the use on slow-moving, heavily loaded open gears.
- It is also used to lubricate rack-and-pinion gears, wire ropes, slides, cams and other machinery in mills and mines and other heavy industries.
- Temperature range: -20°C up to + 120°C, +140°C intermittent.

Advantages

- Castrol Tribol™ OG 500-0 forms a very tough lubricating film on friction surfaces.
- This stable film offers excellent resistance to high loads even at slow speeds. In the FZG special test for grease (A/2.76/50) Castrol Tribol OG 500-0 reaches a scoring load stage of >12 with an extremely low specific wear of <0.20 mg/kWh.
- No additional wear on pistons or plugging of nozzles of automatic spray systems, as Castrol Tribol™ OG 500-0 does not contain solids.
- Regeneration of damaged frictional surfaces can occur on a microscale range.
- The lubricant film is resistant to weather and environmental influences.
- The stable protective lubricant film is easily and economically applied through automatic dispensing systems over a wide temperature range: -20°C up to + 120°C, 140°C intermittent.
- Increased life of machinery and lubricants.
- Extended lube intervals, reduced consumption and consequential reduction of maintenance and repair costs.

Typical Characteristics

Name	Method	Units
NLGI grade	DIN 51818	-
Thickener	-	-
Worked penetration	ASTM D217 / ISO 2137	0.1 mm
Copper strip corrosion test @ 100°C corrosion degree	DIN 51811	-
Base Oil Viscosity @ 40°C / 104°F	ASTM D445 / ISO 3104	mm ² /s
Base Oil Viscosity @ 100°C / 212°F	ASTM D445 / ISO 3104	mm ² /s
Water Resistance @ 90°C	DIN 51807-1	Rating
FZG Gear Scuffing test - A/2.76/50	ISO 14635-3	Rating
FZG Gear Scuffing test - A/2.76/50 change in weight	ISO 14635-3	mg/kWh
Four Ball Wear test - Weld Load	DIN 51350-4A	N

1 mm²/s ^ 1cSt Subject to usual manufacturing tolerances

Additional Information

- CASTROL TRIBOL OG 500-0 should not be mixed with greases of a different thickener.
- Relubrication intervals should be adjusted according to operating conditions

This product was previously called Tribol 5000. The name was changed in 2015.

Tribol™ OG 500-0

23 Oct 2015

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol (UK) Limited, PO BOX 352, Chertsey Road, Sunbury On Thames, Middlesex, TW16 9AW
Orders/Enquiries: 0345 9645111 Technical Enquiries: 0345 082 1719
www.castrol.com/industrial