

Tribol™ GR ES 2

Energy Saving Grease

Description

Castrol Tribol™ GR ES 2 (previously called Longtime™ ES 2) is an energy saving, synthetic high performance grease based on novel thickener-technology.

It has excellent mechanical and shear stability and extraordinary resistance against water and humidity as well as metalworking fluid emulsions.

The carefully selected additive package includes antioxidants, corrosion inhibitors and a unique EP/AW system. The novel polymeric thickener is non-ionic, inert and contributes to an increased film thickness. This, in turn, results in longer life and easier and more secure maintenance. On account of its polymeric nature we can use the lower base oil viscosity instead of a higher base oil viscosity product. This in turn helps reduce the application temperature and leads to energy saving.

Significant drop in temperature has been observed in certain applications.

Due to the inertness of the thickener system, the product is also compatible with most types of conventional lubricating greases. In addition, the technology provides high adhesion and low solubility resulting in excellent resistance to water and aggressive chemicals.

Application

- For lubrication for both sliding- and rolling applications
- The product can be used for consolidation within a plant
- For lubrication of electric motor bearings.
- For Bearing-lubrication even under strong influence of emulsions or water.
- For lubrication of Chucks in Machine tools
- Temperature application range: - 30°C up to 100°C, max 120°C short term peaks.

Advantages

- Lower energy consumption.
- Decreased Operating temperatures.
- Excellent mechanical and shear stability.
- Decreased grease consumption and longer bearing lifetime
- Improved machine availability due to extended grease intervals and reduced downtime.
- Extraordinary resistance against water and metalworking fluid emulsions.
- Opportunity for product consolidation in a manufacturing facility.

Typical Characteristics

Name	Method	Units	Tribol GR ES 2
Colour	Visual	-	Beige
Appearance	Visual	-	Homogenous
Dropping Point	ASTM D566 / ISO 2176	°C/°F	140 / 284
Four Ball Wear test - Weld Load	DIN 51350-4A	N	3000
Flow pressure @ (-30°C / -22°F)	DIN 51805	mBar	1400
Worked Penetration (60 strokes @ 25°C / 77°F)	ASTM D217 / ISO 2137	0.1mm	265 - 295
Worked Penetration (100,000 strokes @ 25°C / 77°F) - change from 60 strokes	ASTM D217 / ISO 2137	0.1mm	50
Roll Stability test - Shear Stability (50 hrs, 80°C / 176°F)	ASTM D1831 (modified)	0.1mm	80
Rust Test - EMCOR (synthetic seawater)	ASTM D6138 / ISO 11007	Rating	0/1
Copper Corrosion (24 hrs, 100°C / 212°F)	ASTM D130 / ISO 2160	Rating	1a
Water Resistance	DIN 51807-1	Rating	1
Water Wash-out	ASTM D1264 / ISO 11009 / DIN 51807-2	% wt loss	2
Oil Separation (168 hrs @ 40°C / 104°F)	IP 121 / DIN 51817	% wt	3
Four Ball Wear test - Wear Scar Diameter	DIN 51350-5E	mm	1.8

Subject usual manufacturing tolerances.

This product was previously called Longtime ES 2. The name was changed 2015.

Tribol™ GR ES 2

11 Oct 2017

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol (UK) Limited, PO BOX 352, Chertsey Road, Sunbury On Thames, Middlesex, TW16 9AW
 Orders/Enquiries: 0345 9645111 Technical Enquiries: 0345 082 1719
www.castrol.com/industrial